

Claims:


1. A piezoelectric element comprising:

a ceramic substrate,

5 a piezoelectric portion made of a piezoelectric ceramic composition containing a $\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3$ - PbZrO_3 - PbTiO_3 ternary system solid solution composition having an average particle diameter of $1 - 10 \mu\text{m}$ with a maximum particle diameter being 5 times as large as the average particle diameter or less and
10 being represented by the following general formula (1) as a main component and 0.05 to 10.0 mass% of NiO, and

an electrode;

wherein said electrode is electrically connected to said piezoelectric portion, and said piezoelectric portion is solidly
15 attached to the ceramic substrate directly or via said electrode.



wherein $0.95 \leq x \leq 1.05$; $0.8 \leq y \leq 1.0$; a, b and c are decimals falling in a range surrounded by $(a,b,c) = (0.550, 0.425, 0.025)$, $(0.550, 0.325, 0.125)$, $(0.375, 0.325, 0.300)$, $(0.100, 0.425, 0.475)$,
20 $(0.100, 0.475, 0.425)$ and $(0.375, 0.425, 0.200)$ in the coordinates with coordinate axes of said a, b and c, and $a+b+c = 1.00$.

2. A piezoelectric element comprising:

a ceramic substrate,


a plurality of piezoelectric portion made of a piezoelectric
25 ceramic composition containing a $\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3$ - PbZrO_3 - PbTiO_3

201090 2622001

ternary system solid solution composition represented by the following general formula (1) as a main component and 0.05 to 10.0 mass% of NiO, and

a plurality of electrodes;

wherein said plurality of piezoelectric portion are laminated with interposing negative electrodes and positive electrodes of said electrodes alternately in each gap between said piezoelectric portions and a lowermost piezoelectric portion is solidly attached to the ceramic substrate directly or via said electrode.



wherein $0.95 \leq x \leq 1.05$; $0.8 \leq y \leq 1.0$; a, b and c are decimals falling in a range surrounded by (a,b,c) = (0.550, 0.425, 0.025), (0.550, 0.325, 0.125), (0.375, 0.325, 0.300), (0.100, 0.425, 0.475), (0.100, 0.475, 0.425) and (0.375, 0.425, 0.200), in the coordinates with coordinate axes of said a, b and c, and $a+b+c = 1.00$.

3. A piezoelectric element according to Claim 2, wherein said ternary system solid solution composition has an average particle diameter of 1 - 10 μm with a maximum particle diameter being 5 times as large as the average particle diameter or less.

4. A piezoelectric element comprising:

a ceramic substrate,

a piezoelectric portion made of a piezoelectric ceramic composition containing a $\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3$ - PbZrO_3 - PbTiO_3 ternary


10072297-060402

system solid solution composition represented by the following general formula (1) as a main component and 0.05 to 10.0 mass% of NiO, and said piezoelectric ceramic composition contain particles having NiO as a main component on the surface and/or

5 in the interior thereof, and

an electrode;

wherein said electrode is electrically connected to said piezoelectric portion, and said piezoelectric portion is solidly attached to the ceramic substrate directly or via said electrode.



wherein $0.95 \leq x \leq 1.05$; $0.8 \leq y \leq 1.0$; a, b and c are decimals falling in a range surrounded by (a,b,c) = (0.550, 0.425, 0.025), (0.550, 0.325, 0.125), (0.375, 0.325, 0.300), (0.100, 0.425, 0.475), (0.100, 0.475, 0.425) and (0.375, 0.425, 0.200), in the coordinates

15 with coordinate axes of said a, b and c, and $a+b+c = 1.00$.

5. A piezoelectric element according to Claim 4, wherein said ternary system solid solution composition has an average particle diameter of 1 - 10 μm with a maximum particle diameter being 5 times as large as the average particle diameter

20 or less.

6. A piezoelectric element according to Claim 4, wherein said particles having NiO as a main component is obtained by subjecting MgO to a solid solution treatment.

7. A piezoelectric element according to Claim 1, wherein Ni

25 is dispersed in said piezoelectric ceramic composition in such a

10072297-060402

concentration gradient that the concentration of Ni becomes higher from the interface between said piezoelectric portion and said substrate towards the thickness direction of the piezoelectric portion.

5 8. A piezoelectric element according to Claim 2, wherein Ni is dispersed in said piezoelectric ceramic composition in such a concentration gradient that the concentration of Ni becomes higher from the interface between said piezoelectric portions and said substrate towards the thickness direction of the
10 piezoelectric portions.

9. A piezoelectric element according to Claim 4, wherein Ni is dispersed in said piezoelectric ceramic composition in such a concentration gradient that the concentration of Ni becomes higher from the interface between said piezoelectric portion and
15 said substrate towards the thickness direction of the piezoelectric portion.

10. A piezoelectric element according to Claim 1, wherein Pb in said piezoelectric ceramic composition is replaced by at least one kind of element selected from the group consisting of Sr, Ca
20 and Ba, by 2 to 10 mole % in the whole Pb.

11. A piezoelectric element according to Claim 2, wherein Pb in said piezoelectric ceramic composition is replaced by at least one kind of element selected from the group consisting of Sr, Ca and Ba, by 2 to 10 mole % in the whole Pb.

25 12. A piezoelectric element according to Claim 4, wherein Pb

10072297.060402

in said piezoelectric ceramic composition is replaced by at least one kind of element selected from the group consisting of Sr, Ca and Ba, by 2 to 10 mole % in the whole Pb.

13. A piezoelectric element according to Claim 1, wherein Pb
5 in said piezoelectric ceramic composition is replaced by La by 0.2 - 1.0 mole % in the whole Pb.

14. A piezoelectric element according to Claim 2, wherein Pb
in said piezoelectric ceramic composition is replaced by La by 0.2 - 1.0 mole % in the whole Pb.

10 15. A piezoelectric element according to Claim 4, wherein Pb
in said piezoelectric ceramic composition is replaced by La by 0.2 - 1.0 mole % in the whole Pb.

16. A piezoelectric element according to Claim 1, wherein said piezoelectric portion has a thickness of 1 to 300 μm .

15 17. A piezoelectric element according to Claim 2, wherein said piezoelectric portions have a thickness of 1 to 300 μm .

18. A piezoelectric element according to Claim 1, wherein said piezoelectric portion has a thickness of 1 to 300 μm .

19. A piezoelectric element according to Claim 1, wherein said
20 substrate has a thickness of 3 μm to 1 mm.

20. A piezoelectric element according to Claim 2, wherein said substrate has a thickness of 3 μm to 1 mm.

21. A piezoelectric element according to Claim 4, wherein said substrate has a thickness of 3 μm to 1 mm.

25 22. A piezoelectric element according to Claim 1, wherein the

10072297-060402

ratio of the thickness of the substrate to the thickness of the piezoelectric portion (the thickness of the substrate / the thickness of the piezoelectric portion) is 0.1 to 30.

23. A piezoelectric element according to Claim 2, wherein the
5 ratio of the thickness of the substrate to the thickness of the piezoelectric portions (the thickness of the substrate / the thickness of the piezoelectric portions) is 0.1 to 30.

24. A piezoelectric element according to Claim 4, wherein the
10 ratio of the thickness of the substrate to the thickness of the piezoelectric portion (the thickness of the substrate / the thickness of the piezoelectric portion) is 0.1 to 30.

25. A piezoelectric element according to Claim 1, wherein a cross-section of said substrate in the thickness direction has a W-like shape having three inflection points.

15 26. A piezoelectric element according to Claim 2, wherein a cross-section of said substrate in the thickness direction has a W-like shape having three inflection points.

27. A piezoelectric element according to Claim 4, wherein a cross-section of said substrate in the thickness direction has a
20 W-like shape having three inflection points.


28. A method for producing a piezoelectric element comprising the steps of:

superposing a piezoelectric material made of a piezoelectric ceramic composition containing a $\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3$ -
25 PbZrO_3 - PbTiO_3 ternary system solid solution composition

10072297-050402

represented by the following general formula (1) as a main component and 0.05 to 10.0 mass% of NiO on a ceramic substrate or on an electrode formed on the ceramic substrate, and

subjecting the superposed piezoelectric material to a thermal treatment in an atmosphere where 0.03 – 0.5 mg/cm³ (NiO conversion amount per unit volume of a space in a container) of a atmosphere-controlling material having the same composition as the piezoelectric material is coexisted.



wherein $0.95 \leq x \leq 1.05$; $0.8 \leq y \leq 1.0$; a, b and c are decimals falling in a range surrounded by (a,b,c) = (0.550, 0.425, 0.025), (0.550, 0.325, 0.125), (0.375, 0.325, 0.300), (0.100, 0.425, 0.475), (0.100, 0.475, 0.425) and (0.375, 0.425, 0.200), in the coordinates with coordinate axes of said a, b and c, and $a+b+c = 1.00$.

29. A method for producing a piezoelectric element comprising the steps of:


superposing a piezoelectric material made of a piezoelectric ceramic composition containing a $\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3$ - PbZrO_3 - PbTiO_3 ternary system solid solution composition represented by the following general formula (1) as a main component and 0.05 to 10.0 mass% of NiO on a ceramic substrate or on an electrode formed on the ceramic substrate, and

subjecting the superposed piezoelectric material to a thermal treatment in an atmosphere;

wherein 0.03 – 0.5 mg/cm³ (NiO conversion amount per

204090 26222001

unit volume of a space in a container) of an atmosphere-controlling material having the same composition as the piezoelectric material is coexisted as a container for housing said electrode on which the piezoelectric material is superposed and a
 5 setter for mounting the piezoelectric material thereon.



wherein $0.95 \leq x \leq 1.05$; $0.8 \leq y \leq 1.0$; a, b and c are decimals falling in a range surrounded by (a,b,c) = (0.550, 0.425, 0.025), (0.550, 0.325, 0.125), (0.375, 0.325, 0.300), (0.100, 0.425, 0.475),
 10 (0.100, 0.475, 0.425) and (0.375, 0.425, 0.200), in the coordinates with coordinate axes of said a, b and c, and $a+b+c = 1.00$.

204090-622401